



Q235

TESTING / PRUEBAS



Q345

Steel L RING System Scaffolding Q235

Andamio Multidireccional Q235

Test No.	Height	Ultimate Load [kN]	Ultimate Load per Leg [kN]	% of Average Ult. Load
1	91.5"	355.341	88.835	3
2	91.5"	357.557	89.389	2
3	91.5"	421.828	105.457	15
4	91.5"	330.076	82.519	10
Average Ultimate Load [kN]		366.201	91.550	
Average Ultimate Load [lbs]		82,322	20,580	
Average Ultimate Load [kgs]		37,341	9,335	


Steel L RING System Scaffolding Q345

Andamio Multidireccional Q345

Test No.	Height	Ultimate Load [kN]	Ultimate Load per Leg [kN]	% of Average Ult. Load
1	91.5"	371.740	92.935	7
2	91.5"	342.930	85.733	1
3	91.5"	345.590	86.398	0
4	91.5"	322.980	80.745	7
Average Ultimate Load [kN]		345.810	86.453	
Average Ultimate Load [lbs]		77,738	19,435	
Average Ultimate Load [kgs]		35,262	8,816	

CAN / CSA-S269.2 -M87

Access Scaffolding for construction Purposes (Section 11.3.4)



PLAN VIEW
VISTA EN PLANTA

Test witnessed by:



AUG 19 2009



AFTER TEST / DESPUES DE